



TEST REPORT

Number : SHAT00671174


Applicant : BETA TEXTILES CO., LIMITED
6E, FUGANG MANSION, NO.36 RENMIN
ROAD(M), ZHANGJIAGANG, JIANGSU, CHINA
Attn : SUN MIN

Date : Jun 10, 2008

Sample Description As Declared :

No. Of Sample : One
Fibre Content : 100% Wool
Material : Jersey Knitted Fabric
Finishing : -
End Uses : -
Colour : Black
Style No. : -
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Applicant's Provided Care Instruction/Label:



Date Received/Date Test Started : June 5, 2008

Conclusion:

Dimensional Stability To Commercial Drycleaning	M
Color Fastness To Drycleaning	M
Bursting Strength As Received	M
Pilling Resistance As Received	M
Counts Of Yarn	#

Note : M = Commercially Acceptable
N/A = Not Applicable

F = Fail

= No Comment

Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai

Lilian Ding
General Manager



TEST REPORT

Number : SHAT00671174

Tests Conducted (As Requested By The Applicant)

1 Dimensional Stability To Commercial Drycleaning In Perchloroethylene:

After One Dryclean

Length -1.3%
Width -0.6%

Remark : (+) Means Extension and (-) Means Shrinkage

2 Color Fastness To Drycleaning (AATCC 132-1989, 30 Minutes Mechanical Wash At 85°F In Perchloroethylene):

Color Change 4.5

3 Bursting Strength As Received (ASTM D3786-2006, Mullen Type Burster):

40.8 lbf/in²

4 Pilling Resistance As Received (ASTM D3512-2005, Random Tumbler):

After A 30-Minute Test

Rating 4

5 Counts Of Yarn (ASTM D1059-2001):

13.7 texX2(72.8 Nm/2)

Remark : tex = Tex count
Nm = Metric count