



TEST REPORT

Number : SHAT00671204


Applicant : BETA TEXTILES CO., LIMITED  
6E, FUGANG MANSION, NO.36 RENMIN  
ROAD(M), ZHANGJIAGANG, JIANGSU, CHINA  
Attn : SUN MIN

Date : Jun 10, 2008

Sample Description As Declared :

No. Of Sample : One  
Fibre Content : -  
Material : Knitted Fabric  
Finishing : -  
End Uses : -  
Colour : Navy/White  
Style No. : -  
Order No./PO No. : -  
Buyer's Name : -  
Manufacturer's Name : -  
Ref. : -

Applicant's Provided Care Instruction/Label:



Date Received/Date Test Started : June 5, 2008

Conclusion:

Dimensional Stability To Commercial Drycleaning M  
Color Fastness To Drycleaning M  
Pilling Resistance As Received M

Note : M = Commercially Acceptable F = Fail # = No Comment  
N/A = Not Applicable

Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai

Lilian Ding  
General Manager



TEST REPORT

Number : SHAT00671204

Tests Conducted (As Requested By The Applicant)

1 Dimensional Stability To Commercial Drycleaning In Perchloroethylene:

After One Dryclean

Length	-2.2%
Width	+0.6%

Remark : (+) Means Extension and (-) Means Shrinkage

2 Color Fastness To Drycleaning (AATCC 132-1989, 30 Minutes Mechanical Wash At 85°F In Perchloroethylene):

Color Change	4.5
--------------	-----

3 Pilling Resistance As Received (ASTM D3512-2005, Random Tumbler):

After A 30-Minute Test

Rating	3.5
--------	-----

---