



TEST REPORT

Number : SHAT00692626


Applicant : BETA TEXTILES CO., LIMITED  
6E, FUGANG MANSION, NO.36 RENMIN  
ROAD(M), ZHANGJIAGANG, JIANGSU, CHINA  
Attn : DAVID SUN

Date : Jun 27, 2008

Sample Description As Declared :

No. Of Sample : One  
Fibre Content : 50% Cotton 50% Polyester  
Material : Knitted Fabric  
Finishing : -  
End Uses : Garments  
Colour : Navy  
Style No. : -  
Order No./PO No. : -  
Buyer's Name : -  
Manufacturer's Name : -  
Ref. : -

Applicant's Provided Care Instruction/Label :



Date Received/Date Test Started : Jun 24, 2008

Conclusion:

Dimensional Stability To Washing M  
Color Fastness To Washing M  
Pilling Resistance As Received M

Note : M = Commercially Acceptable  
N/A = Not Applicable

F = Fail

# = No Comment

Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai

Lilian Ding  
General Manager



TEST REPORT

Number : SHAT00692626

Tests Conducted (As Requested By The Applicant)

- 1 Dimensional Stability To Washing (AATCC 135-2004, Test No. (1)IIA(II), 12 Minutes Machine Wash At 80°F, Normal Cycle, Followed By Tumble Dry - Delicate):

After Three Washes

Length	-3.1%
Width	+0.6%

Remark : (+) Means Extension and (-) Means Shrinkage

- 2 Color Fastness To Washing (45 Minutes Mechanical Wash At 105°F In 0.15% AATCC WOB Detergent Solution With 50 Steel Balls):

Color Change	4.5
Color Staining	
-Acetate	4.5
-Cotton	4.5
-Nylon	4.5
-Polyester	4.5
-Acrylic	4.5
-Wool	4.5

- 3 Pilling Resistance As Received (ASTM D3512-2005, Random Tumbler):

After A 30-Minute Test

Rating	3.5
--------	-----